



ACA 30 CYANOACRYLATE ADHESIVE

PRODUCT DESCRIPTION

ACA 30 is a superfast Cyanoacrylate adhesive of low viscosity. It is designed for the bonding of materials that have relatively inactive surfaces and is excellent for the bonding of elastomers and rubbers with excellent humidity resistance.

APPLICATIONS

A general purpose grade of the superfast range. Bonds all rubber materials in seconds. Bonding of rubber and metal Components. Bonding of fabric to metals. Seals and O rings.

CHARACTERISTICS:

- > **Single component adhesive 100% solvent free**
- > **Superfast setting**
- > **Good humidity resistance**
- > **Low viscosity, good working properties**

PERFORMANCE DATA, TYPICAL VALUES

Tensile shear strength

Material	Fixture Time	Strength (N/mm ²)
ABS/ABS	10 Seconds	3*
Nitrile	5 Seconds	2*
EPDM	10 Seconds	3*
PVC	10 Seconds	3
Mild Steel (degreased)	20 Seconds	10
Aluminium (degreased)	15 Seconds	5

*Substrate Failure



ACA 30 CYANOACRYLATE ADHESIVE

PHYSICAL PROPERTIES OF LIQUID ADHESIVE

Monomer	Modified ethyl cyanoacrylate
Appearance	Colourless
Specific Gravity	1.05
Viscosity @ 25°C (Brookfield)	15-30 cPs
Flash Point (Cleveland open cup)	> 85°C
Shelf Life(Stored below 25°C)	12 months minimum
Toxicity	Non-toxic

PHYSICAL PROPERTIES OF CURED ADHESIVE

Refractive index (ND20)	1.46
Hardness (Rockwell)	85
Specific resistance OHM/cm	8×10^{12}
Dielectric constant @ 1MHZ	3.44
Softening Point	150°C
Working temperature range	-60°C to + 80°C

DIRECTIONS FOR USE

Ensure surfaces are clean and dry, apply adhesive to one surface. Press surfaces together and hold for 10 seconds or as indicated below. Cure speed is rapid so exercise care when aligning. Cure performance can be enhanced if necessary, by using selected activators.

TYPICAL BONDING TIMES

Plastics	5 - 60 seconds depending on substrate
Rubbers	2 - 20 seconds depending on substrate
Metals (degreased)	10 - 60 seconds depending on substrate

LIMITATIONS

Ensure surfaces are degreased prior to bonding. Ensure surfaces are close fitting. This product is not suitable for permanent glass bonding, or applications where the bonded joint maybe immersed in water



ACA 30 CYANOACRYLATE ADHESIVE

RELATIVE HUMIDTY CONDITIONS

Where possible the working environment should have a relative humidity of 50%+

CAUTION

Prior to use consult relevant Material Safety Data Sheet. When continuously used local fume extraction is recommended. Contains cyanoacrylate ester. Use in a well ventilated environment. In the event of inadvertent skin bonding separate bonded skin issue carefully by peeling apart gently with a blunt instrument. Preferably after soaking in warm soapy water. Keep out of reach of children.

STORAGE

Store in original sealed upright container between +3°C and 20°C in a dry area out of direct sunlight. The lower the temperature the longer the ultimate shelf life, but bring to room temperature before use.

PACKAGING

Available in 20g, 50g and 500g packs.
Other packs available upon request.

FURTHER INFORMATION

Please contact Amber Composites for additional information.

This is not a specification. The information given in this data sheet in relation to the performance, storage and other characteristics of the product is based on results gained from experience and tests and is believed to be accurate. Given, however, that conditions of use and storage will vary, Amber Composites will not be liable for any loss or damage resulting from reliance upon such information. The purchaser is recommended to carry out his own tests to establish the suitability of the product for its particular purpose. The use of the product in certain processes may require third party consent.