



ACA AMBLACK ADHESIVE

PRODUCT DESCRIPTION

ACA Amblack 300 is a tough semi-flexible single part superfast Cyanoacrylate adhesive providing a more flexible bondline and thereby greater resistance to peel cleavage and thermal shock.

APPLICATIONS

Rubber to rubber bonding, rubber to metal bonding, electronic and speaker parts, toy assemblies and sports goods etc.

CHARACTERISTICS:

- > Single component adhesive 100% solvent free
- > Bonds at room temperature
- > Good humidity resistance and tough flexible bond

PERFORMANCE DATA, TYPICAL VALUES

Tensile shear strength

Material

Tensile shear strength (ASTM D1002)
Impact strength (ASTM 950)
Peel strength

Strength (N/mm²)

20 - 24 (2.8-3.4k lbf/in²)
20 - 24 (8-12 ft. lb/in²)
3,5 - 5,0 (20-30 lb/in²)

Tensile testing of natural rubber to rubber bonds, produced substrate failure.

PHYSICAL PROPERTIES OF LIQUID ADHESIVE

Monomer	Modified ethyl
Appearance	Black
Specific Gravity	1.1
Viscosity @ 25°C (Brookfield)	3,000 cPs
Flash Point (Cleveland open cup)	> 85°C
Shelf Life(Stored below 25°C)	8 Months minimum
Toxicity	Non-toxic



ACA AMBLACK ADHESIVE

PHYSICAL PROPERTIES OF CURED ADHESIVE

Specific resistance OHM/cm	3 X 10 ¹⁵
Dielectric constant @ IMC	4.3 @ 1000Hz
Softening Point	165°C
Working temperature range	-60°C to + 130°C

DIRECTIONS FOR USE

Ensure surfaces are clean and dry, apply adhesive to one surface. Press surfaces together and hold for 10 seconds or as indicated below. Cure speed is rapid so exercise care when aligning. Cure performance can be enhanced if necessary, by using selected activators.

TYPICAL BONDING TIMES

Plastics	5 - 60	seconds depending on substrate
Rubbers	2 - 20	seconds depending on substrate
Metals (degreased)	10 - 60	seconds depending on substrate

LIMITATIONS

Ensure surfaces are degreased prior to bonding
Ensure surfaces are close fitting
This product is not suitable for permanent glass bonding, or applications where the bonded joint maybe immersed in water

RELATIVE HUMIDTY CONDITIONS

Where possible the working environment should have a relative humidity of 50%+



ACA AMBLACK ADHESIVE

CAUTION

Prior to use consult relevant Material Safety Data Sheet. When continuously used local fume extraction is recommended. Contains Cyanoacrylate Ester. Use in a well ventilated environment. In the event of inadvertent skin bonding separate bonded skin issue carefully by peeling apart gently with a blunt instrument. Preferably after soaking in warm soapy water. Keep out of reach of children.

STORAGE

Store in original sealed upright container between +3°C and 20°C in a dry area out of direct sunlight. The lower the temperature the longer the ultimate shelf life, but bring to room temperature before use.

PACKAGING

Available in 20g, 50g and 500g packs.
Other packs available upon request.

FURTHER INFORMATION

Please contact Amber Composites for additional information.

This is not a specification. The information given in this data sheet in relation to the performance, storage and other characteristics of the product is based on results gained from experience and tests and is believed to be accurate. Given, however, that conditions of use and storage will vary, Amber Composites will not be liable for any loss or damage resulting from reliance upon such information. The purchaser is recommended to carry out his own tests to establish the suitability of the product for its particular purpose. The use of the product in certain processes may require third party consent.