



## ARALDITE 204

One Component Foaming Adhesive

### PRODUCT DESCRIPTION

Araldite 204 is a one-pack paste adhesive developed primarily for bonding segments of honeycomb core material, and for bonding the edges of the core to structural edge members, in bonded sandwich panels. The cured Araldite 204 provides a shear-carrying connection across these discontinuities within the panel, and thus preserves the structural integrity of the panel.

Araldite 204 is intended for use in applications where the maximum working temperature does not exceed 90°C. It can be used, however, at temperatures up to 120°C if it is not required to sustain significant working loads.

#### CHARACTERISTICS:

- Extrudable paste form
- Expands during cure to fill voids
- 120°C curing
- Core splicing adhesives

### TYPICAL PRODUCT DATA

Properties	Araldite 204 (uncured)
Color (visual)	Black
Specific gravity	1.1
Viscosity Pa.s	3500
Shelf life (0°C) months	12
Flashpoint °C	>100

### PROCESSING

When Araldite 204 is used for bonding sections of Aeroweb honeycomb in sandwich structures, there is generally no need to pretreat the edges of the core segments.

Aluminum honeycomb which has been machined or has become soiled in any other way should be thoroughly degreased before bonding. For maximum bond strength, the core segments should be cut slightly oversize (about one cell row or equivalent on each edge), and the edges flattened back, collapsing the overlapping cells, to produce a continuous closed edge at the honeycomb. This closed edge must be degreased, by rinsing with trichloroethylene or other appropriate solvent.



## ARALDITE 204

### One component Foaming Adhesive

This type of pre-treatment is not practical with non-metallic Aeroweb cores; these should be cut slightly oversize so that, when assembled, they exert an outward pressure on the panel edges. Solvent degreasing is not recommended, so it is essential when handling non-metallic honeycomb to take care to avoid any contamination.

Pretreat the edge members of sandwich panels in accordance with the instructions given for the adhesive used to bond the edge members to the facing skins. No further pre-treatment is needed for bonding with the Araldite 204.

### APPLICATION

Araldite 204 may be applied by extrusion from a suitable pressurised gun, or by spreading with a spatula or other appropriate tool. After removal from cold storage Araldite 204 should be left to warm up naturally to room temperature before opening the container.

Apply Araldite 204 to one side of each joint only. When applied by extrusion a suitable spread is obtained by applying beads of paste, 6mm diameter, evenly spaced at approximately 13 mm centre distance along the core edge parallel to the core faces. If the adhesive is applied by spatula, try to obtain an even spread approximately 2.5mm thick. Care should be taken that large masses of adhesive do not occur.

### ASSEMBLY

After applying the adhesive, push the core segments firmly together and complete the panel assembly as quickly as possible to prevent it from being disturbed. Providing the components are suitably clamped to prevent relative movement, the assembly may be set aside before the adhesive is cured, but bonding must be completed within the safe working life of each adhesive system used in the assembly.

### CURING

Araldite 204 is cured by heating to a minimum temperature of 120°C. For optimum properties the assembly should be held at the curing temperatures as follows.

Curing Temperature°C	120	150	170
Curing time (minimum)	1 hour	30 min	20 min
Expansion (nominal)	50 – 125%	75 – 175%	100-200%

Heat up rate is not critical, but when curing at a high temperature (e.g. 170°C) it is advisable to keep the rate of temperature rise below 10°C per minute. Allow adequate time for heat to penetrate the whole assembly so that the adhesive is properly cured throughout the depth of the panel.

Temperatures should be held within limits of  $\pm 5^\circ\text{C}$  to cure the Araldite 204 in the times stated.



## ARALDITE 204

One component Foaming Adhesive

---

When autoclave bonding assemblies containing Araldite 204 the vacuum line should preferably be opened to atmosphere in order to ensure even expansion of the foam.

### DOUBLE LAP SHEAR STRENGTH

Typical minimum individual values, determined on production batches. (1.6 mm glue line thickness)

At 22°C	-	12 mPa
At 80°C	-	10 mPa

These values are for information only and do not constitute a specification.

---

### STORAGE

Store Araldite 204 in a cool dry place. The adhesive has a storage life of 12 months when stored at 0°C plus a cumulative 'out' life of 3 months at room temperature. The expiry date of the safe storage life for the material is stated on the label of each pack.

---

### HANDLING SAFETY

These products are generally quite harmless to handle provided that certain precautions normally taken when handling chemicals are observed. The uncured materials must not, for instance, be allowed to come into contact with foodstuffs or food utensils, and measures should be taken to prevent the uncured materials from coming in contact with the skin, since people with particularly sensitive skin may be affected. The wearing of impervious rubber or plastic gloves will normally be necessary; likewise the use of eye protection. The skin should be thoroughly cleansed at the end of each working period by washing with soap and warm water. The use of solvents is to be avoided. Disposable paper - not cloth towels - should be used to dry the skin. Adequate ventilation of the working area is recommended.

For further information refer to Material Safety Data Sheet.

---

### FURTHER INFORMATION

Please contact Amber Composites for additional information.

This is not a specification. The information given in this data sheet in relation to the performance, storage and other characteristics of the product is based on results gained from experience and tests and is believed to be accurate. Given, however, that conditions of use and storage will vary, Amber Composites will not be liable for any loss or damage resulting from reliance upon such information. The purchaser is recommended to carry out his own tests to establish the suitability of the product for its particular purpose. The use of the product in certain processes may require third party consent.