

RAKU-TOOL[®] CC-6507

Close Contour Casting

Cast Polyurethane

PC - Rev.-Status: 01- 2007/04/25

Page 1 of 2

Key Properties

- Dense surface structure
- Very easily machined
- Good dimensional stability
- Good abrasion resistance and impact strength

Applications

- Pattern plates and core boxes
- Machined negatives and positives
- Models, molds and tools
- Hammer forms and jigs

Advantages of Close Contour Casting

- Quicker machining, less tool wear and less wastage through close contour shape
- Less manual finishing required as the surface is seamless, smooth, very dense and free from bubbles through our vacuum casting process
- No handling of liquid chemistry, concentration on milling technology
- Good dimensional stability as the material exhibits little stresses and is isotropic like board material
- High quality standard

Mechanical Properties

			CC-6507
Color	visual		Olive
Density	ISO 1183	g/cm ³	1.40
Shore hardness D	ISO 868		85 – 90
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	50 – 55
Deflection temperature, HDT	ISO 75	°C	75 – 80
Compressive strength	ISO 604	MPa	85 – 95
Compressive modulus	ISO 604	MPa	3500 – 4000

Processing

The product should have a temperature of 20°C – 25°C during processing.

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL[®] CC-6507
Close Contour Casting
Cast Polyurethane

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.
