

# CENUSIL® M 385

RTV-2 Silicone Rubber / Mold Making

Supplied by

## AMBERCOMPOSITES

### Characteristics

Pourable, condensation-curing, two-component silicone rubber that vulcanizes at room temperature.

### Special characteristics

- Medium Shore A hardness (approx. 25)
- Good flowability and self-deaeration
- High tear strength
- Excellent long-term stability of the mechanical properties of the vulcanizate

### Application

- Mold making

### Processing

CENUSIL® M 385 is cured by adding Catalyst T 37 for long and intermediate pot-life and curing time, or Catalyst T 12 for fast curing.

### Pot lifes and curing times

Catalyst	Pot life, approx. [min]	Curing time (tack-free), approx. [h]
3 % T 37	60	14
4 % T 37	40	10
3 % T 12	40	6
4 % T 12	20	4

The pot life is the period of time at 23 °C / 50 % rel. humidity during which the catalyzed mix to attain a viscosity of 60,000 mPa s and still be just pourable.

Comprehensive instructions are given in our leaflet "WACKER RTV-2 Silicone Rubber - Processing."

### Product data (uncured)

Property	Test method	Unit	Value
Color			White
Density at 23 °C		[g/cm <sup>3</sup> ]	1.21
Viscosity at 23 °C, after stirring	ISO 3219	[mPa s]	25,000

### Product data (catalyzed with 3 wt % Catalyst T 37)

Property	Test method	Unit	Value
Viscosity at 23 °C	ISO 3219	[mPa s]	20,000

### Product data (cured)

Property	Test method	Unit	Value
Density at 23 °C in water	ISO 2781	[g/cm <sup>3</sup> ]	1.20
Hardness, Shore A	ISO 868		25
Tensile strength	ISO 37	[N/mm <sup>2</sup> ]	3
Elongation at break	ISO 37	[%]	300
Tear strength	ASTM D 624 B	[N/mm]	5
Linear shrinkage		[%]	0.6

With 3 wt % Catalyst T 37, after 4 days at 23 °C / 50 % rel. humidity

These figures are only intended as a guide and should not be used in preparing specifications.

## Storage

CENUSIL® M 385 should be stored between 5 °C and 30 °C in the originally sealed container. The 'Best use before end' date of each batch appears on the product label.

Catalysts T 12 and T 37 should be stored in the sealed original bottles between 5 °C and 25 °C.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

## Safety information

Being a condensation-curing silicone rubber, CENUSIL® M 385 contains only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Catalysts T 12 and T 37 contain a tetraorganotin compound, is flammable (flash points 53 °C) and may cause irritation in contact with eyes and skin. Adequate protective measures are required.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

## Additional information

Please visit our website [www.wacker.com](http://www.wacker.com)

*Supplied by*

**AMBERCOMPOSITES**

94 Station Road, Langley Mill  
Nottingham, NG16 4BP United Kingdom  
T: +44 (0)1773 530899 F: +44 (0)1773 768687  
E: [sales@ambercomposites.com](mailto:sales@ambercomposites.com)  
[www.ambercomposites.com](http://www.ambercomposites.com)

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

**WACKER**

and CENUSIL® are registered trademarks of Wacker-Chemie AG.

Version 4.00 from 30-08-07 replaces Version 3.00 from 22-06-07

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG  
WACKER-SILICONES  
Hanns-Seidel-Platz 4  
81737 Munich, Germany

[www.wacker.com](http://www.wacker.com)  
[silicones@wacker.com](mailto:silicones@wacker.com)