

Supplied by

AMBERCOMPOSITES



Release Innovation™

PRODUCT DATA

Chemlease® 1367

Semi-Permanent Release Agent

Description

Chemlease® 1367 is a rapid curing semi-permanent mold release agent that provides multiple releases with virtually no transfer to the molded part.

Chemlease® solvent carriers contain no Class I or II registered ozone depleting substances.

Application

Mold Preparation:

1. Clean mold surface to remove all traces of waxes, releases and sealers.
2. Clean mold with Mold Cleaner EZ.
3. Apply Chemlease® 15 Sealer to new or porous molds (see Chemlease® 15 Sealer technical data sheet for details).

Instructions for base coats:

To the cleaned/sealed mold surface:

1. Using a wetted clean 100% cotton cloth (we recommend Chemlease® Cotton Cloth) or fine mist spray pattern, wipe or spray on a smooth, wet, (not runny) continuous film over the entire mold surface.
2. Do not wipe film off, allow to dry on its own and cure for 10 minutes.
3. If puddling or dripping occurs, (usually the case for heavy application or cold molds) wipe off any excess on the mold surface with a clean, dry cotton cloth
4. Apply a total of 3-5 coats per the above instructions.
5. Allow final coat to cure for 30 minutes at room temperature. Cure is instant at 120°C or higher.

TOUCH UP COATS:

Reapply one light coat as required and cure as for final coat.

TIPS: If final time can be extended to one hour or longer at room temperature or mold can be heated to 65°C or higher for 30 minutes, this will further enhance the quality of release and the number of releases between applications.

Storage

Do not store at temperatures above 38°C. Keep container tightly sealed to prevent evaporation and/or moisture contamination. If stored in cold temperatures, allow product to warm to room temperature prior to use. Do not use, if the expiry date has been exceeded.

Handling

We believe Chemlease® 1367 has a low degree of hazard when used as intended. For more information, request a copy of Chem-Trend's Material Safety Data Sheet.

Packaging

Chemlease® 1367 is available in containers filled with 0,76 kg; 3,8 kg; 13,3 kg and 150 kg.

Further Information

Request information on our complete range of materials for this industry.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

The information contained in this document is given in good faith based on our current knowledge. It is only an indication and in no way binding, particularly as regards infringement of or prejudice to third party rights through the use of our products. Chem-Trend warrants only that its products will meet its sales specifications. This information must on no account be used as a substitute for necessary prior tests which alone can ensure that a product is suitable for a given use. Users are requested to check that they are in possession of the latest version of this document and Chem-Trend is at their disposal to supply any additional information.

Produced: BMI 26.10.2006
Sales

Checked and Approved: Dr. Ingo Däke – 27.10.2006
Technical Department

Chem-Trend (Deutschland) GmbH ▪ Robert-Koch-Str. 27 ▪ 22851 Norderstedt ▪ Phone: +49-40-529 55-0 ▪ Fax: +49-40-529 55-2111

www.chemtrend.com ▪ email: service@chemtrend.de