

RAKU-TOOL[®] EC-2401 / EH-2904, EH-2905, EH-2906

Epoxy Casting System

Supplied by

With mineral fillers, variable reactivity

AMBERCOMPOSITES

PC - Rev.-Status: 01- 2006/06/14

Page 1 of 2

Key Properties

- Universally applicable
- Low sedimentation
- Flows very well
- Reactivity can be adjusted by using different hardeners
- Easily workable
- Good reproduction of detail

Applications

- Foundry patterns
- Copy models
- Direct casting (negatives)
- Jigs and fixtures
- Working models for the ceramics industry
- Galvano bath models

Processing Properties

			EC-2401	EH-2904	EH-2905	EH-2906
Color	visual		Ivory	Clear	Clear	Clear
Mix ratio		parts by weight	100	20		
			100		20	
			100			20
Density	ISO 1183	g/cm ³	1.75	1.00	1.01	1.01
Viscosity at 25 °C	ISO 2555	m Pa.s	60000-80000	60-110	50-100	50-100

			EC-2401 EH-2904	EC-2401 EH-2905	EC-2401 EH-2906
Mix viscosity at 25 °C	ISO 2555	m Pa.s	2800-3800	2500-3500	2500-3500
Pot life at 25 °C	1000 ml	min	45	90	180
Max. layer thickness		mm	10	20	80
Demold time		h	12	16	18

Cured / Mechanical Properties

Cure: 7 days at RT or 14h at 40°C			EC-2401 EH-2904	EC-2401 EH-2905	EC-2401 EH-2906
Appearance	visual		Ivory	Ivory	Ivory
Density	ISO 1183	g/cm ³	1.6	1.6	1.6
Shore hardness D	ISO 868		85-90	85-90	85-90
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	50-55	50-55	50-55
Glass Transition Temperature, T _g	DSC	°C	60-65	50-55	45-50
Compressive strength	ISO 604	MPa	95-100	100-105	100-105
Compressive modulus	ISO 604	MPa	6000-6500	5500-6000	6500-6700
Flexural strength	ISO 178	MPa	75-80	70-75	80-85
Flexural modulus	ISO 178	MPa	6000-6500	6000-6500	6000-6500
Linear shrinkage*		mm / m	0.2	1.0	0.4
Abrasion	mm ³ /100R	Taber			

*measured on maximum layer thickness as stated above

RAKU-TOOL® EC-2401 / EH-2904 / EH-2905 / EH-2906

Epoxy Casting System

With mineral fillers, variable reactivity

PC - Rev.-Status: 01- 2006/06/14

Page 2 of 2

Processing

Mix the two components thoroughly in the ratio indicated.

Degassing and /or post-curing will improve final properties.

The processing and material temperature should be between 20-25 °C.

Packaging

RAKU-TOOL® EC-2401	6 x 1.4 kg / 10 kg
RAKU-TOOL® EH-2904	6 x 0.280 kg / 2 kg / 25 kg
RAKU-TOOL® EH-2905	6 x 0.280 kg / 2 kg / 25 kg
RAKU-TOOL® EH-2906	6 x 0.280 kg / 2 kg / 25 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG
Albstr. 37 • D-72661 Grafenberg
T +49 (0) 7123 9342-1600
F +49 (0) 7123 9342-1666
E info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.