

RAKU-TOOL[®] EL-2200 / EH-2900

Epoxy Laminating and Multipurpose System

RT curing, unfilled, low viscosity

PC - Rev.-Status: 01- 2006/06/15

Page 1 of 2

Key Properties

- Room temperature curing
- Good compatibility with glass fibres and fillers
- With short glass fibres (6mm) also suitable for coupling layers
- Backing resin with mineral and metal fillers

Applications

- General tool building and tooling aids
- Binder for Quartz sand for metal forming tools
- Backing structures

Processing Properties

			EL-2200	EH-2900
Color	visual		Clear	Clear
Mix ratio		parts by weight	100	20
Density	ISO 1183	g/cm ³	1.10	1.03
Viscosity at 25 °C	ISO 2555	m Pa.s	2000-2300	450-750

			EL-2200 / EH-2900
Mix viscosity at 25 °C	ISO 2555	m Pa.s	1000-1300
Pot life at 25 °C	500 ml	min	70
Max. layer thickness		mm	8
Demold time		h	16

Cured / Mechanical Properties

Cure: 7 days at RT or 14h at 40°C			EL-2200 / EH-2900
Appearance	visual		Clear
Density	ISO 1183	g/cm ³	1.1
Glass Transition Temperature, T _g	DSC	°C	45-50
Flexural strength	ISO 178	MPa	90
Flexural modulus	ISO 178	MPa	2200

Processing

The processing and material temperature should be between 20-25 °C.

Mix the two components thoroughly in the ratio indicated. Impregnate each layer of cloths to construct the laminate layer by layer. Post-curing will improve final properties.

RAKU-TOOL® EL-2200 / EH-2900

Epoxy Laminating and Multipurpose System

RT curing, unfilled, low viscosity

Packaging

RAKU-TOOL® EL-2200	25 kg / 220 kg / 1000 kg
RAKU-TOOL® EH-2900	5 kg / 22 kg / 200 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG
Albstr. 37 • D-72661 Grafenberg
T +49 (0) 7123 9342-1600
F +49 (0) 7123 9342-1666
E info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.