

Supplied by

AMBERCOMPOSITES

ELASTOSIL® M 4500

RTV-2 Silicone Rubber / Mold Making

Characteristics

Pourable, condensation-curing, two-component silicone rubber that vulcanizes at room temperature.

Special characteristics

- Very low Shore A hardness (approx. 14)
- Good flowability and self-deaeration
- High tear strength
- Extremely great extensibility and elasticity
- Excellent long-term stability of the mechanical properties of the vulcanizate
- High resistance to polyester resins

Application

Due to its good mechanical properties of the cured material as well as its high resistance to polyester resins, ELASTOSIL® M 4500 is particularly suitable as a mold-making material for reproducing models with very pronounced undercuts in polyester resins.

The very low modulus of ELASTOSIL® M 4500 proves to be particularly advantageous for all molding applications where only low demolding forces may be applied because the models or castings have low mechanical strength.

Other materials, such as plaster or wax, may also be cast without any problems from molds made of ELASTOSIL® M 4500.

Due to the very low hardness of the cured rubber and its excellent ink transfer performance, ELASTOSIL® M 4500 is an ideal base material for producing printing pads.

Product data (uncured)

Property	Test method	Unit	Value
Color			White
Density at 23 °C		[g/cm ³]	1.21
Viscosity at 23 °C, after stirring	ISO 3219	[mPa s]	30,000

Product data (catalyzed with 3 wt % Catalyst T 12)

Property	Test method	Unit	Value
Viscosity at 23 °C	ISO 3219	[mPa s]	25,000

Product data (cured)

Property	Test method	Unit	Value
Density at 23 °C in water	ISO 2781	[g/cm ³]	1.20
Hardness Shore A	ISO 868		14
Tensile strength	ISO 37	[N/mm ²]	3.0
Elongation at break	ISO 37	[%]	450
Tear strength	ASTM D 624 B	[N/mm]	> 15
Linear shrinkage		[%]	0.6

With 3 wt % Catalyst T 12, after 4 days at 23 °C / 50 % rel. humidity.

These figures are only intended as a guide and should not be used in preparing specifications.

Processing

ELASTOSIL® M 4500 is cured by adding Catalyst T 12.

Catalyst	Pot life, approx. [min]	Curing time (tack-free), approx. [h]
3 % T 12	70	6-7
4 % T 12	30	4-5

The pot life is the period of time at 23 °C / 50 % rel. humidity during which the catalyzed mix to attain a viscosity of 60,000 mPa s and still be just pourable.

Comprehensive instructions are given in our leaflet "WACKER RTV-2 Silicone Rubber - Processing."

Detailed information on other mold-making compounds in the ELASTOSIL® M range is contained in our brochure "ELASTOSIL® M. Mold-Making Compounds For Maximum Precision".

Storage

ELASTOSIL® M 4500 should be stored between 5 °C and 30 °C in the tightly closed original container. The 'Best use before end' date of each batch appears on the product label.

Catalysts T 12 should be stored in the sealed original bottles between 5 °C and 25 °C.

Storage beyond the date specified on the label does not necessarily mean that the product is no longer usable. In this case however, the properties required for the intended use must be checked for quality assurance reasons.

Safety information

Being a condensation-curing silicone rubber, ELASTOSIL® M 4500 contains only constituents that over many years have proved to be neither toxic nor aggressive. Special handling precautions are therefore not required, i.e., only the general industrial hygiene regulations apply.

Catalysts T 12 contains a tetraorganotin compound, is flammable (flash point 53 °C) and may cause irritation in contact with eyes and skin. Adequate protective measures are required.

Detailed safety information is contained in each Material Safety Data Sheet, which can be obtained from our sales offices.

Additional information

Please visit our website www.wacker.com

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
 Nottingham, NG16 4BP United Kingdom
 T: +44 (0)1773 530899 F: +44 (0)1773 768687
 E: sales@ambercomposites.com
www.ambercomposites.com

The data presented in this leaflet are in accordance with the present state of our knowledge, but do not absolve the user from carefully checking all supplies immediately on receipt. We reserve the right to alter product constants within the scope of technical progress or new developments. The recommendations made in this leaflet should be checked by preliminary trials because of conditions during processing over which we have no control, especially where other companies' raw materials are also being used. The recommendations do not absolve the user from the obligation of investigating the possibility of infringement of third parties' rights and, if necessary, clarifying the position. Recommendations for use do not constitute a warranty, either express or implied, of the fitness or suitability of the products for a particular purpose.

The management system has been certified according to DIN EN ISO 9001 and DIN EN ISO 14001

WACKER

and ELASTOSIL® are registered trademarks of Wacker Chemie AG.

Version 7.00 from 30-08-07 replaces Version 6.00 from 11-04-07

For technical, quality, or product safety questions, please contact:

Wacker Chemie AG
 WACKER-SILICONES
 Hanns-Seidel-Platz 4
 D-81737 Munich, Germany

www.wacker.com
silicones@wacker.com