

RAKU-TOOL[®] EP-2300 / EH-2930

Modeling Paste

Multipurpose Paste

PC - Rev.-Status: 01- 2006/05/11

Page 1 of 2

Key Properties

- Easily shaped with wood working tools
- Good adhesion to most supporting structures

Applications

- Styling and Design models
- Master models
- Patterns

Processing Properties

			EP-2300	EH-2930
Color	visual		Brown	Brown
Mix ratio		parts by weight	100	100
		parts by volume	100	100
Density	ISO 1183	g/cm ³	0.63	0.64

			EP-2300 / EH-2930
Pot life at 25 °C	1000 ml	min	60
Layer thickness		mm	40
Workable after (at 25°C)		h	16

Cured / Mechanical Properties

Cure: 7 days at RT or 14h at 40°C			EP-2300 / EH-2930
Appearance	visual		Brown
Density	ISO 1183	g/cm ³	0.65
Shore hardness D	ISO 868		60
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	55-60
Transition temperature, T _g	DSC	°C	70
Compressive strength	ISO 604	MPa	25
Flexural strength	ISO 178	MPa	25
Flexural modulus	ISO 178	MPa	800-850
Linear shrinkage		mm / m	

RAKU-TOOL® EP-2300 / EH-2930

Modelling Paste
Multipurpose Paste

Processing

The processing and material temperature should be between 20-25 °C, never below 18 °C.

Mix the two components thoroughly in the ratio indicated.

Avoid applying over 40 mm at once, for thicker layers it is recommended to apply the 2nd layer after the first one has gelled.

Small quantities can be mixed by hand (with a strong wooden spatula). For larger quantities the use of a mixing machine is recommended.

Packaging

RAKU-TOOL® EP-2300	15 kg
RAKU-TOOL® EH-2930	15 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG
Albstr. 37 • D-72661 Grafenberg
T +49 (0) 7123 9342-1600
F +49 (0) 7123 9342-1666
E info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.