

# LORD® 403, 406 and 410 Adhesives with Accelerator 19 or 19GB

Supplied by

**AMBERCOMPOSITES**

## Description

LORD® 403, 406 and 410 acrylics in combination with Accelerator 19 or 19GB replace welding, brazing, riveting and other mechanical fastening methods especially in low-temperature environments subject to high impact or high peel loads. LORD 403, 406 and 410 acrylics are available in a range of working times to accommodate a wide variety of process requirements.

LORD 403, 406 and 410 acrylics when mixed with Accelerator 19 or 19GB create adhesives that will bond a wide variety of prepared or unprepared metals and engineered plastics. The mixed adhesives are specifically formulated to provide the highest impact and peel strengths available in a room temperature curing adhesive.

LORD 403, 406 and 410 acrylics can be mixed with either Accelerator 19 or Accelerator 19GB. Accelerator 19 improves the high temperature resistance of LORD 403, 406 and 410 acrylics, and is available in off-white or black. Accelerator 19GB allows precise control of the adhesive bondline thickness due to its content of glass beads. Accelerator 19GB is available in off-white or red.

For further detailed information on Accelerator 19 and Accelerator 19GB, refer to the applicable data sheet.

## Features and Benefits

**Versatile** – bonds a wide range of unprepared metals with minimal substrate preparation; bonds difficult plastics such as XENOY®.

**Temperature Resistant** – performs at temperatures from -40 to +300°F (-40 to +149°C).

**Environmentally Resistant** – resists dilute acids, alkalis, solvents, greases, oils, moisture, salt spray and weathering; provides excellent resistance to UV exposure.

**Non-Sag** - remains in position when applied on vertical or overhead surfaces, allowing for greater process flexibility.

## Application

**Surface Preparation** – Remove grease, loose contamination or poorly adhering oxides from metal surfaces. Normal amounts of mill oils and drawing compounds usually do not present a problem in

## Typical Properties\*

	<b>403</b>	<b>406</b>	<b>410</b>
Appearance	Off-white to Tan Paste	Off-white to Tan Paste	Off-white to Tan Paste
Viscosity, cP @ 77°F (25°C) Brookfield	100,000-280,000	100,000-300,000	100,000-350,000
Density			
lb/gal	9.25-9.55	9.1-9.7	9.15-9.65
(kg/m <sup>3</sup> )	(1108-1144)	(1090-1162)	(1096-1156)
Flash Point, °F (°C)	59 (15)	59 (15)	59 (15)

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

adhesion. Most plastics require a simple cleaning before bonding. Some may require abrading for optimum performance.

**Mixing** – Mix LORD 403, 406 or 410 acrylic with the proper amount of Accelerator 19 or 19GB. Handheld cartridges will automatically dispense the correct volumetric ratio of each component. Even color distribution visually indicates a thorough mix. Once mixed, the acrylic adhesive cures rapidly.

**Applying** – Apply adhesive using handheld cartridges or automatic meter/mix/dispense equipment.

- Handheld Cartridges
  1. Load the cartridge into the applicator gun and remove the end caps.
  2. Level the plungers by expelling a small amount of adhesive to ensure both sides are level.
  3. Attach mixing top and expel a mixer's length of adhesive.
  4. Apply adhesive to substrate and mate the parts within the working time of the adhesive. Clamp in position until adhesive reaches handling strength.

Do not re-expose adhesive to air once parts are mated. Mated parts should be repositioned by sliding to achieve proper alignment.

- Meter/Mix/Dispense Equipment  
Contact your LORD representative if assistance is needed using this equipment.

**Curing** – Cure begins immediately once acrylic and accelerator are mixed. Depending on acrylic, handling strength is achieved within 4-60 minutes. Complete cure will take 24 hours at room temperature. Mating surfaces must be held in contact during the entire cure period. Cure rate can be accelerated by applying modest heat. If heat cured, do not exceed temperatures of 150°F (66°C). Cured adhesive is colored to visually indicate a full cure; cure color depends on the accelerator used.

**Cleanup** – Clean equipment and tools prior to the adhesive cure with solvents such as isopropyl alcohol, acetone or methyl ethyl ketone (MEK). Once adhesive is cured, heat the adhesive to 400°F (204°C) or above to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed. Some success may be achieved with commercial epoxy strippers.

## Typical Properties\* of Acrylic Mixed with Recommended Accelerator

	403	406	410
Mix Ratio, Acrylic to Accelerator			
by Weight	3:1	3:1	3:1
by Volume	4:1	4:1	4:1
Solids Content, %	100	100	100
Working Time, minutes @ 75°F (25°C)	2-4	6-10	20-30
Time to Handling Strength, minutes @ 75°F (25°C) 50 psi Shear	4-6	12-17	~60
Mixed Appearance			
A19	Tan Paste	Tan Paste	Tan Paste
A19 Black	Gray Paste	Gray Paste	Gray Paste
A19GB	Tan Paste	Tan Paste	Tan Paste
A19GB Red	Light Red Paste	Light Red Paste	Light Red Paste
Cured Appearance			
A19	Tan to Green	Tan to Green	Tan to Green
A19 Black	Black	Black	Black
A19GB	Tan to Green	Tan to Green	Tan to Green
A19GB Red	Dark Red	Dark Red	Dark Red

\*Data is typical and not to be used for specification purposes.

# LORD TECHNICAL DATA

## Typical Cured Properties

	403	406	410
Tensile Strength at Break, psi (MPa) ASTM D638, modified	4650 (32.1)	4650 (32.1)	4650 (32.1)
Elongation, % ASTM D638, modified	30	30	30
Young's Modulus, psi (MPa) ASTM D638, modified	130, 000 (896.3)	130, 000 (896.3)	130, 000 (896.3)
Glass Transition Temperature, °F (°C) ASTM E1640-99, by DMA	162 (72)	162 (72)	162 (72)

## Bond Performance

Substrates	Aluminum to Aluminum	Galvanized Steel to Galvanized Steel	Powder Coated Steel to Powder Coated Steel	ABS to ABS
Lap Shear @ Room Temperature, psi (MPa) Failure Mode	2650 (18.3) C	2500 (17.2) C	2800 (13.3) C	1000 (6.9) SB
Lap Shear @ Hot Strength [180°F (82°C)], psi (MPa) Failure Mode	1980 (13.7) TLC	1830 (12.8) TLC	1050 (7.2) CF	350 (2.4) SB
T-Peel, pli (N/mm) Failure Mode	25 (4.4) C	22 (3.9) C	26 (4.6) C	— —
500 hours Salt Spray Exposure, psi (MPa) Test after 24 hours Failure Mode	2650 (18.3) TLC	2500 (17.2) TLC	1470 (10.1) CF	— —
14 days @ 100°F (38°C), 100% Relative Humidity, psi (MPa) Failure Mode	2900 (20.0) C	2450 (16.9) C	2400 (16.5) C	— —
Test @ -30°F (-34°C) Failure Mode	2500 (17.2) C	2800 (19.3) C	3300 (22.8) CF	— —

### Substrate

Aluminum, 0.032" thick 6061T6  
Galvanized Steel, 0.030" thick electrogalvanized  
Powder Coated Steel, 0.035" thick, polyester on cold rolled steel  
Acrylonitrile Butadiene Styrene (ABS), 0.125" thick hair cell ABS

### Surface Treatment

Dry Rag Wipe  
Dry Rag Wipe  
Dry Rag Wipe  
Dry Rag Wipe

### Bonded Parameters

Metal Lap Shears (ASTM D1002)  
ABS Lap Shears (ASTM D3163)  
T-Peel (ASTM D1876 modified)

### Bond Area

1.0"x0.5"  
1.0"x1.0"  
1.0"x3.0"

### Film Thickness

0.010"  
0.010"  
0.010"

### Cure

24 hr @ RT  
24 hr @ RT  
72 hr @ RT

### Mix Ratio

4:1 by Volume  
4:1 by Volume  
4:1 by Volume

### Failure Mode Definition

Cohesive Failure  
Coating Failure  
Stock Break  
Thin Layer Cohesive Failure

### Abbreviation

C  
CF  
SB  
TLC

# LORD TECHNICAL DATA

## Shelf Life/Storage

Shelf life is six months from date of shipment when stored at 40-50°F (4-10°C) in original, unopened container or as indicated on package labeling. Allow product to return to room temperature before using. Protect acrylic from exposure to UV light.

LORD 403, 406 and 410 acrylics are flammable. Do not store or use near heat, sparks or open flame.

## Cautionary Information

Before using this or any LORD product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

*For industrial/commercial use only.* Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Supplied by

**AMBERCOMPOSITES**

94 Station Road, Langley Mill  
Nottingham, NG16 4BP United Kingdom  
T: +44 (0)1773 530899 F: +44 (0)1773 768687  
E: sales@ambercomposites.com  
www.ambercomposites.com

Values stated in this technical data sheet represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Support Center.

Information provided herein is based upon tests believed to be reliable. In as much as LORD Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, LORD Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party, including but not limited to any product end-user. Nor does the company make any express or implied warranty of merchantability or fitness for a particular purpose concerning the effects or results of such use.

LORD is a registered trademark and "Ask Us How" is a trademark of LORD Techmark, Inc., a subsidiary of LORD Corporation. XENOY is a registered trademark of General Electric Company.

LORD provides valuable expertise in adhesives and coatings, vibration and motion control, and magnetically responsive technologies. Our people work in collaboration with our customers to help them increase the value of their products. Innovative and responsive in an ever-changing marketplace, we are focused on providing solutions for our customers worldwide . . . Ask Us How.

### LORD Corporation World Headquarters

111 Lord Drive  
Cary, NC 27511-7923  
USA

**Customer Support Center**  
+1 877 ASK LORD (275 5673)

www.lord.com