



MULTIPREG HX70

Low Temperature Curing Epoxy Tooling Prepreg

HX70 is an epoxy resin system that can be pre-impregnated into high performance fibers such as carbon, glass and kevlar. It is a highly reactive system that offers shortened cure cycles and low temperature cycles. After a suitable post-cure an end-use temperature of 180°C (356°F) is achieved.

CHARACTERISTICS:

- > Low initial cure temperature
- > Unsupported post-cure
- > Excellent drape for complex shapes
- > High glass transition temperature
- > 30 hours work life at ambient
- > 6 months storage life
- > Low coefficient of thermal expansion
- > Low volatile content

The processing parameters and instructions contained in this technical datasheet are to be used in accordance with the detailed instructions provided in the document "Autoclave-Cured Tools Using MULTIPREG HX SERIES" available from Amber Composites.

RESIN PROPERTIES	
Density	1.23 g/cm ³ (76.7lbs/ft ³) at 23°C (73.4°F)
Tg (DMTA) after 190°C (374°F) post-cure	Onset: 190°C (374°F) Peak Tan δ: 215°C (419°F)
Typical C.T.E. for a carbon tool	3.0*(1.65) X10 ⁻⁶ /°C (°F)

*CTE is dependent on construction and processing. Figures quoted are based on standard 1-8-1 quasi-isotropic tooling laminates.



MULTIPREG HX70


Low Temperature Curing Epoxy Tooling Prepreg

INITIAL MINIMUM CURE TIMES

Temperature °C (°F)	Time (hrs)
30 (86)	35
35 (95)	23
40 (104)	15
45 (113)	10
50 (122)	6.5
55 (131)	4.25

CURING CYCLES

Initial Minimum Cure Schedules - HX70





MULTIPREG HX70

Low Temperature Curing Epoxy Tooling Prepreg


POST-CURE

Post-cure schedule A:

Ramp	1°C (1.8°F) / min to 60°C (140°F)	Dwell for 2 hours
Ramp	1°C (1.8°F) / min to 90°C (194°F)	Dwell for 1 hour
Ramp	1°C (1.8°F) / min to 120°C (248°F)	Dwell for 1 hour
Ramp	1°C (1.8°F) / min to 150°C (302°F)	Dwell for 1 hour
Ramp	1°C (1.8°F) / min to 170°C (338°F)	Dwell for 1 hour
Ramp	1°C (1.8°F) / min to 190°C (374°F)	Dwell for 6 hours

Cool to 50°C (122°F) at 2.5°C/min (4.5°F/min)

Post-cure Schedule A






MULTIPREG HX70

Low Temperature Curing Epoxy Tooling Prepreg

An alternative post-cure schedule may also be used as follows:



REINFORCEMENTS AVAILABLE

Fiber type	Weight (gsm)	Weave style	Molded thickness (mm)	Std. resin content w/o
High Strength Carbon 3k	205	2/2 Twill	0.23	46 (surface ply)
High Strength Carbon 12k	650	2/2 Twill	0.62	35

Other fabrics and resin weights available on request.



MULTIPREG HX70

Low Temperature Curing Epoxy Tooling Prepreg

CAUTION

MULTIPREG HX70 prepreg contains a reactive resin system and care must be taken to avoid exothermic heating during the initial cure. Avoid exceeding 55°C (131°F) initial cure.

STORAGE

Shelf life is 30 hours at ambient temperature 20°C (68°F)

Refrigerated storage life is 6 months at -18°C (0°F)

To avoid moisture condensation: Following removal from cold storage, allow prepreg to reach room temperature before opening the polythene bag.

HANDLING SAFETY

Observe established precautions for handling epoxy resins and fibrous materials. Ensure adequate ventilation, wear gloves, goggles, and protective clothing.

For further information refer to Material Safety Data Sheet.

FURTHER INFORMATION

For further processing information refer to, "Autoclave-Cured Tools Using MULTIPREG HX SERIES" available from Amber Composites.

Please contact Amber Composites for additional information.

This is not a specification. The information given in this data sheet in relation to the performance, storage and other characteristics of the product is based on results gained from experience and tests and is believed to be accurate. Given, however, that conditions of use and storage will vary, Amber Composites will not be liable for any loss or damage resulting from reliance upon such information. The purchaser is recommended to carry out his own tests to establish the suitability of the product for its particular purpose. The use of the product in certain processes may require third party consent.