

RAKU-TOOL[®] PC-3406 (Polyol) / PH-3906 (Isocyanate)

Casting System

Flexible, RT Curing, Two Component Polyurethane

PC - Rev.-Status: 01- 2009/06/26

Page 1 of 2

Key Properties

- High mechanical properties
- High tear strength
- Flows well
- Soft / flexible
- Excellent resistance to mechanical influences (vibration) etc.

Applications

- Structural molds
- Closed plaster molds for the ceramics industry

Processing Properties

			PC-3406	PH-3906
Color	visual		Beige	Yellow / Brown
Mix ratio		pb weight	100	12
		pb volume	100	14
Density	ISO 1183	g/cm ³	1.42	1.15
Viscosity at 25 °C	ISO 2555	m Pa.s	2500-3000	20-40

			PC-3406 / PH-3906
Mix viscosity at 25 °C	ISO 2555	m Pa.s	-
Pot life at 25 °C	1000 ml	min	25-30
Max. layer thickness		mm	20
Demouldable after		h	24

Cured / Mechanical Properties**Cure: 7 days at RT or 14 h at 40 °C**

			PC-3406 / PH-3906
Appearance	visual		Beige
Density	ISO 1183	g/cm ³	1.1
Shore Hardness A	ISO 868		55-60
Glass Transition Temperature, T _g	DSC	°C	-
Tensile strength	ISO 527	MPa	3,5 – 4,0
Elongation at break	ISO 527	%	50 - 70
Linear shrinkage		mm / m	-
Abrasion	Taber	mm ³ /100R	-

RAKU-TOOL® PC-3406 (Polyol) / PH-3906 (Isocyanate)

Casting System

Flexible, RT Curing, Two Component Polyurethane

PC - Rev.-Status: 01- 2009/06/26

Page 2 of 2

Processing

The A component needs to be stirred well before use as some fillers might be prone to sedimentation. Mix the two components thoroughly in the ratio indicated carefully avoiding any air entrapment. Degassing and /or post-curing will improve final properties.

The processing and material temperature should be between 20-25 °C.

Packaging

RAKU-TOOL® PC-3406	25 kg, 200 kg
RAKU-TOOL® PH-3906	3 kg, 24 kg

Storage

In temperature controlled environments (20 °C - 25 °C) the original containers can be stored for at least 6 months. Both components are moisture sensitive and containers therefore need to be kept tightly sealed. The storage temperature for the hardener should not be below 20 °C as at 15 °C it might crystallize.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com