

RAKU-TOOL[®] PR-3600 (Polyol) / PH-3904 (Isocyanate)

Prototyping System

Fast curing, two component Polyurethane

PC - Rev.-Status: 01- 2009/06/26

Page 1 of 2

Key Properties

- Simulates rubber
- Short demold time
- Very high elongation at break

Applications

- Functional prototype parts
- Short run production
- Rapid Prototyping

Processing Properties

			PR-3600	PH-3904
Color	visual		Black	Yellowish
Mix ratio		pb weight	100	33
		pb volume	100	28
Density	ISO 1183	g/cm ³	1.04	1.21
Viscosity at 25 °C	ISO 2555	m Pa.s	1000-1500	20-40

			PR-3600 / PH-3904
Pot life at 25 °C		sec	90
Layer thickness		mm	4
Demold time (RT)		min	15-25

Cured / Mechanical Properties

Cure: 7 days at RT or 14h at 40°C			PR-3600 / PH-3904
Appearance	visual		Black
Density	ISO 1183	g/cm ³	1.14
Shore hardness A	ISO 868		65-70
Deflection temperature, HDT	ISO 75	°C	-
Tensile strength	ISO 527	MPa	7-9
Elongation at break	ISO 527	%	380-430
Flexural strength	ISO 178	MPa	-
Flexural modulus	ISO 178	MPa	-
Impact strength Charpy (edgewise)	ISO 179-1/1eU	KJ/m ²	-
Tear strength	DIN 53515	N/mm	13-18
Abrasion	Taber	mm ³ /100R	23-28
Linear shrinkage		mm / m	-

RAKU-TOOL® PR-3600 (Polyol) / PH-3904 (Isocyanate)

Prototyping System

Fast curing, two component Polyurethane

PC - Rev.-Status: 01- 2009/06/26

Page 2 of 2

Processing

The processing and material temperature should be between 20-25 °C.

The A component needs to be stirred well before use as some fillers might be prone to sedimentation.

Hand mixing or manual processing of the material is not recommended. To process the material it is recommended to use a two component low pressure casting machine with a static dynamic mixer. The material must be cast into the mold during the pot life time but not too fast to avoid any air entrapment. The recommended material temperature **must** be observed. Too high or low a material temperature will change the viscosity (high/low) and have a direct influence on the mixing ratio set up on the machine. Changes in the mixing ratio will result in faults in the finished part.

Packaging

RAKU-TOOL® PR-3600

5 kg

RAKU-TOOL® PH-3904

5 kg / 20 kg / 25 kg

Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill

Nottingham, NG16 4BP United Kingdom

T: +44 (0)1773 530899 F: +44 (0)1773 768687

E: sales@ambercomposites.com

www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG
Robert-Bosch-Str. 8-10 • D-72661 Grafenberg
T +49 (0) 7123 9342-1600
F +49 (0) 7123 9342-1666
E info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.