



Redux® 312

Modified epoxy film adhesive

Product Data

Supplied by

AMBERCOMPOSITES

Description

Redux 312 is a high strength 120°C curing film adhesive, suitable for metal to metal bonding and sandwich constructions, where operating temperatures of up to 100°C may be experienced.

A supported version, Redux 312/5, is available with a woven nylon carrier for bond line thickness control.

Features

- Short cure cycle - cures in 30 minutes at 120°C
- Good mechanical performance up to 100°C
- Suitable for composite to composite bonding
- Low volatile content (solventless process)

Applications

- Metal to metal bonding
- Sandwich constructions
- Composite to composite bonding

Forms

Grey flexible film adhesive, available in 5 areal weights; 4 in unsupported form and one with a woven nylon carrier.

Product Description	Areal Weights g/m ²	Roll Width mm	Standard Roll m ²
Redux 312	70	533	60
Redux 312UL	100	533	60
Redux 312L	150	533	50
Redux 312	300	533	40
Redux 312/5	293	533	40

Instructions For Use

Pretreatment

It is essential that all substrates to be used are free of contamination and are in as ideal a state for bonding as possible. As pretreatment varies significantly depending on the substrates used, please refer to the Hexcel Composites publication Redux Bonding Technology for optimum procedures.

If there is to be a delay between the pretreatment and bonding of aluminium, the pretreated surface should be protected with Redux 112 or Redux 140 surface pretreatment protection solution to conserve the optimum bonding surface. This will enable bonding to be delayed for up to 2 weeks without deterioration of the pretreated surface. The correct application of Redux 112 or Redux 140 should not alter the bonding performance of Redux 312 (for full application details consult the relevant data sheet).



Redux 312

Application

1. Allow sufficient time for the adhesive to warm to room temperature (15°C - 27°C) before removing the protective polythene.
2. Cut the film to the shape and size required.
3. Remove the release paper and position the adhesive on the prepared bonding surface.
4. Remove the polythene backing sheet.
5. Complete the joint assembly and apply pressure while the adhesive is being cured. For sandwich structures the pressure application should be selected to suit the type of core used. After the adhesive has cured it is advisable to maintain pressure on the bonded assembly until it has cooled sufficiently to be handled without discomfort.

Curing

Redux 312 should be cured at $120 \pm 5^\circ\text{C}$ for 30 minutes to obtain optimum properties. Enough time should be allowed for heat to penetrate through the assembled parts to ensure that the adhesive reaches that temperature before timing starts. Cure pressures of around 100 - 350 kPa and heat up rates of approximately 5°C per minute are recommended during cure. After curing it is recommended that components are cooled to below 70°C before releasing the pressure.

Mechanical Properties

All the performance values given in this data sheet are based on experimental results obtained during testing under laboratory conditions. They are typical values expected for Redux 312 prepared and cured as recommended and under the conditions indicated. They do not and should not constitute specification minima.

Metal Bonding Strengths

Redux 312 at areal weights of 70, 100, 150 and 300 g/m², and Redux 312/5 at areal weight 293 g/m², were used to bond Alclad 2024-T3 aluminium test specimens; the aluminium was pretreated in accordance with DTD 915B (ii) (chromic/sulphuric acid pickling). The honeycomb tests used Hexcel's 7.9-1/4-40 (5052) T aluminium honeycomb.

Test	Test Temperature °C	Redux 312 70g/m ²	Redux 312 100g/m ²	Redux 312 150g/m ²	Redux 312 300g/m ²	Redux 312/5
Lap Shear Strength MPa	22	37	39	42	43	38
	70	33	32	38	39	29
	80	27	32	35		
	100			17	30	
Bell Peel N/25mm	22		230	245	230	245
Climbing Drum Peel N/76mm	22		190	350	710	510
Flatwise Tensile MPa	22		5.4	7.0	9.1	8.3

Storage

Redux 312 has been formulated for maximum storage life consistent with its high performance. Certain precautions, however, will help to enhance that storage life as follows:

1. When stored at room temperature (less than 27°C) it should be kept on a horizontal mandrel passed through the tube core on which the roll is wound. This avoids the risk of local thinning of the film under the weight of the roll.
2. When storing under refrigeration the original packaging should be retained if possible. When returning to the refrigerator after use it is essential to protect the film with a water vapour barrier packaging material such as polythene.
3. On withdrawal from the refrigerator the water vapour barrier packaging should not be removed until the roll of adhesive has reached room temperature. This may take up to 24 hours depending on the size of the roll and the temperature involved (failure to observe this will result in the film becoming damp).
4. The film should be handled with care whilst in the frozen state since it will be brittle and easily cracked.

On receipt, Redux 312 will have a storage life of at least 12 months at -18°C plus an additional shop life of 1 month at below 27°C.

Volatile content

Redux 312 has a very low volatile content, usually well below 1%. In practice, the loss in weight when cured is negligible and emission of volatile products is not of practical significance.

Associated products

Redux 112 and Redux 140 surface pretreatment protection solutions (primer)
Redux 212/NA and 206/NA foaming film adhesives

Handling and safety precautions

In common with all Redux adhesives in film form, Redux 312 is particularly free from handling hazards for the following reasons:

- Film is covered on both sides by protective release paper and polythene sheet which are not removed until final component assembly. It should be cut to shape before removing the protective coverings and virtually no handling of the film is necessary.
- Virtually tack-free (dry) at normal room temperature. The film is dependent on elevated temperature for wetting-out the adherend surfaces.
- Volatile-free at normal room temperature.
- Splash-free, leak-free, spillage-free.

However, the usual precautions necessary when handling synthetic resins should be observed. A Material Safety Data Sheet for Redux 312 is available on request.



Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

Release Certification

The Quality System at Hexcel Composites Duxford has been certified to ISO 9001 by Lloyd's Register Quality Assurance, and is approved by the UK Civil Aviation Authority and Ministry of Defence. Certificates of Conformity and Test Reports can be issued for batches of Redux 312 on request.

Important

All information is believed to be accurate but is given without acceptance of liability. Users should make their own assessment of the suitability of any product for the purposes required. All sales are made subject to our standard terms of sale which include limitations on liability and other important terms.

©Copyright Hexcel Composites
Publication RTA027a (Oct 2002)

For More Information

Hexcel Composites is a leading worldwide supplier of composite materials to aerospace and other demanding industries. Our comprehensive product range includes:

- Carbon, glass, aramid and hybrid prepregs
- Honeycomb cores
- Structural film adhesives
- Honeycomb sandwich panels
- Special process honeycombs
- RTM materials

For further information, please contact your nearest sales office, or visit our website at www.hexcelcomposites.com

Australia

Suite 2, 86 Grimshaw Street
Greensborough, Victoria 3088
Tel: 61 3 9432 7100
Fax: 61 3 9432 7200

China

Room B707, Yin Hai Bldg.
250 Cao Xi Rd
Shanghai 200233
Tel: 86 21 6483 6741/2
Fax: 86 21 6483 6744

Japan - Joint Venture

DIC - Hexcel Limited
Room 603, Santsu-Mori Bldg.
2-22-1 Nishi - Shimbashi
Minato-Ku, Tokyo 105
Tel: 81 3 5401 0271
Fax: 81 3 5401 0270

USA

101 East Ridge Drive, Suite 102
Danbury, CT 06810
Tel: 1 203 798 8311
Fax: 1 203 798 8161

Austria

Industriestrasse 1
A-4061, Pasching
Tel: 43 (0)7229 7720
Fax: 43 (0)7229 772299

France

ZI La Plaine, B.P.27 Dagneux
01121 Montluel CEDEX
Tel: 33 (0)4 72 25 26 27
Fax: 33 (0)4 72 25 27 30

Spain

Bruselas, 10 - 16
Polig. Ind. "Ciudad de Parla"
28980 Parla, Madrid
Tel: 34 91 664 4900
Fax: 34 91 698 4914

USA

42705 Grand River
Suite 201
Novi, MI 48375
Tel: 1 248 344 8688
Fax: 1 248 305 9760

Belgium

Rue Trois Bourdons, 54
B-4840 Welkenraedt
Tel: 32 87 307 411
Fax: 32 87 882 895

Germany

Postfach 1560
21655 Stade
Tel: 49 4141 7879-00
Fax: 49 4141 7879-01

United Kingdom

Duxford, Cambridge
CB2 4QD
Tel: 44 (0)1223 833141
Fax: 44 (0)1223 838808

USA

2350 Airport Freeway, Suite 550
Bedford, TX 76022-6027
Tel: 1 817 315 3939
Fax: 1 817 571 8629

Brazil

Av. J. Guilhermino, 474/72
S.J.Campos, SP 12210-130
Tel: 55 12 3941 2242
Fax: 55 12 3923 1186

Italy

Via San Cristoforo, 44
21047 Saronno (VA)
Tel: 39 02 96709082
Fax: 39 02 9600809

USA

11711 Dublin Blvd.
Dublin, CA 94568-2832
Tel: 1 925 551 4900
Fax: 1 925 828 9202

USA

16310 NE 80th Street, Suite 102
Redmond, WA 98052
Tel: 1 425 558 4400
Fax: 1 425 861 5847