

# RAKU-TOOL<sup>®</sup> Repair Pastes

## Repair Pastes for boards

### RT curing

PC - Rev.-Status: 01- 2006/01/23

Page 1 of 2

**Key Properties**

- Similar density and hardness to board material
- RT curing

**Applications**

- To repair boards

**Processing Properties** To repair styling boards with a density < 0,55 g/cm<sup>3</sup>

			UP-4300 / UH-4900
Color	visual		Light brown
Mix ratio		pbw	100 : 1-3
Pot life at 25 °C		min	4-6
Minimum curing time		min	25-30

**Processing Properties** To repair modelings boards with a density 0,55-0,72 g/cm<sup>3</sup>

			UP-4310 / UH-4900
Color	visual		Brown
Mix ratio		pbw	100 : 1-3
Pot life at 25 °C		min	4-6
Minimum curing time		min	25-30

**Working boards with a density of 1,0 – 1,7 g-cm<sup>3</sup> can be repaired with adhesive bonded inserts.**

**Processing**

**The processing and material temperature should be between 20-25 °C.**

Mix the two components thoroughly and apply by spatula.

## RAKU-TOOL<sup>®</sup> Repair Pastes

Repair Pastes for boards

RT curing

PC - Rev.-Status: 01- 2006/01/23

Page 2 of 2

### Packaging

RAKU-TOOL<sup>®</sup> UP-4300 / UH 4900

Multipack 6 x 1.96 kg / 6 x 0.04 kg

RAKU-TOOL<sup>®</sup> UP-4310 / UH-4900

Multipack 6 x 1.96 kg / 6 x 0.04 kg

### Storage

Original containers should be kept tightly sealed and stored at ambient temperatures (15°C to 30°C). If properly stored the products have the shelf-life indicated on the product label.

Partly used containers should always be sealed appropriately and used up as soon as possible.

### Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

*Supplied by*

**AMBERCOMPOSITES**

94 Station Road, Langley Mill  
Nottingham, NG16 4BP United Kingdom  
T: +44 (0)1773 530899 F: +44 (0)1773 768687  
E: sales@ambercomposites.com  
www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG  
Albstr. 37 • D-72661 Grafenberg  
T +49 (0) 7123 9342-1600  
F +49 (0) 7123 9342-1666  
E info@rampf-tooling.com

[www.raku-tool.com](http://www.raku-tool.com)

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.