

RAKU-TOOL[®] WB-1222**Board Material****Polyurethane Board for Tools and Molds**

PC - Rev.-Status: 01- 2006/01/06

Page 1 of 2

Key Properties

- Very easily machined
- Good heat resistance
- High impact strength, good edge strength
- High abrasion resistance

Applications

- Pattern plates
- Core boxes
- Tooling jigs
- Hammer forms

Mechanical Properties

			WB-1222
Color	visual		Green
Density	ISO 1183	g/cm ³	1.22
Shore hardness D	ISO 868		75 – 85
Coefficient of thermal expansion	ISO 11359	10 ⁻⁶ K ⁻¹	80 – 85
Deflection temperature, HDT	ISO 75	°C	80 – 90
Compressive strength	ISO 604	MPa	60 – 70
Flexural strength	ISO 178	MPa	70 – 80

Processing

The product should have a temperature of 20°C – 25°C during processing.

Packaging

RAKU-TOOL [®] WB-1222	1000 x 500 x 50 mm 1000 x 500 x 100 mm
--------------------------------	---

Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

RAKU-TOOL[®] WB-1222

Board Material

Polyurethane Board for Tools and Molds

Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

Supplied by

AMBERCOMPOSITES

94 Station Road, Langley Mill
Nottingham, NG16 4BP United Kingdom
T: +44 (0)1773 530899 F: +44 (0)1773 768687
E: sales@ambercomposites.com
www.ambercomposites.com

RAMPF Tooling GmbH & Co. KG
Albstr. 37 • D-72661 Grafenberg
T +49 (0) 7123 9342-1600
F +49 (0) 7123 9342-1666
E info@rampf-tooling.com

www.raku-tool.com

Our recommendations on the use of the material are based on many years of experience and current scientific and practical knowledge. They are, however, provided without any obligation on our part and do not relieve the buyer of the need for suitability tests. They do not constitute a legal relationship, nor are any protected third party rights whatsoever affected thereby.