

# RAKU-TOOL<sup>®</sup> WB-1404

## Board Material

### Polyurethane Board for Tools and Molds

PC - Rev.-Status: 01- 2009/06/24

Page 1 of 2

#### Key Properties

- Dense surface structure
- Very easily machined
- Good dimensional stability
- Good abrasion resistance and impact strength
- Can be polished

#### Applications

- Pattern plates and core boxes
- Machined negatives and positives
- Models, molds and tools
- Hammer forms and jigs

#### Mechanical Properties

			WB-1404
Color	visual		Olive
Density	ISO 1183	g/cm <sup>3</sup>	1.40
Shore hardness D	ISO 868		85 – 90
Coefficient of thermal expansion	ISO 11359	10 <sup>-6</sup> K <sup>-1</sup>	50 – 55
Deflection temperature, HDT	ISO 75	°C	75 – 80
Compressive strength	ISO 604	MPa	85 – 95
Flexural strength	ISO 178	MPa	80 – 90

#### Processing

The product should have a temperature of 20°C – 25°C during processing.

#### Packaging

RAKU-TOOL<sup>®</sup> WB-1404

1000 x 500 x 50 mm  
 1000 x 500 x 75 mm  
 1000 x 500 x 100 mm

#### Storage

The material should be stored flat and in a dry place. Temperature variations should be avoided during storage and transportation.

**RAKU-TOOL<sup>®</sup> WB-1404**

Board Material

Polyurethane Board for Tools and Molds

---

### Handling Precautions

Good workplace ventilation is to be ensured during processing. At the same time, the employer's liability insurance association's industrial hygiene safety regulations regarding the handling of reaction resins and their hardeners are to be observed. Please take heed of the appropriate safety data sheets.

---

**For information on adhesives and repair pastes see the corresponding individual technical data sheets.**

*Supplied by*

**AMBERCOMPOSITES**

94 Station Road, Langley Mill  
Nottingham, NG16 4BP United Kingdom  
T: +44 (0)1773 530899 F: +44 (0)1773 768687  
E: sales@ambercomposites.com  
www.ambercomposites.com